




THE DATASHEET OF 06035A471JAT2A

C0G (NP0) Dielectric

General Specifications



C0G (NP0) is the most popular formulation of the "temperature-compensating," EIA Class I ceramic materials. Modern C0G (NP0) formulations contain neodymium, samarium and other rare earth oxides.

C0G (NP0) ceramics offer one of the most stable capacitor dielectrics available. Capacitance change with temperature is $0 \pm 30 \text{ ppm}/^\circ\text{C}$ which is less than $\pm 0.3\%$ C from -55°C to $+125^\circ\text{C}$. Capacitance drift or hysteresis for C0G (NP0) ceramics is negligible at less than $\pm 0.05\%$ versus up to $\pm 2\%$ for films. Typical capacitance change with life is less than $\pm 0.1\%$ for C0G (NP0), one-fifth that shown by most other dielectrics.







PART NUMBER (SEE PAGE 4 FOR COMPLETE PART NUMBER EXPLANATION)



0805	5	A	101	J	A	T	2	A
Size (L" x W")	Voltage 6.3V = 6 10V = Z 16V = Y 25V = 3 50V = 5 100V = 1 200V = 2 250V = V 500V = 7	Dielectric C0G (NP0) = A	Capacitance Code (In pF) 2 Sig. Digits + Number of Zeros	Capacitance Tolerance B = $\pm 10 \text{ pF}$ ($< 10 \text{ pF}$) C = $\pm 25 \text{ pF}$ ($< 10 \text{ pF}$) D = $\pm 50 \text{ pF}$ ($< 10 \text{ pF}$) F = $\pm 1\%$ ($\geq 10 \text{ pF}$) G = $\pm 2\%$ ($\geq 10 \text{ pF}$) J = $\pm 5\%$ K = $\pm 10\%$	Failure Rate A = Not Applicable	Terminations T = Plated Ni and Sn Contact Factory For 1 = Pd/Ag Term 7 = Gold Plated NOT RoHS COMPLIANT	Packaging 2 = 7" Reel 4 = 13" Reel U = 4mm TR (01005)	Special Code A = Std. Product


Contact Factory For Multiples

NOTE: Contact factory for availability of Termination and Tolerance Options for Specific Part Numbers. Contact factory for non-specified capacitance values.



C0G (NP0) Dielectric

Specifications and Test Methods


Parameter/Test		NP0 Specification Limits	Measuring Conditions	
Operating Temperature Range		-55°C to +125°C	Temperature Cycle Chamber	
Capacitance		Within specified tolerance	Freq.: 1.0 MHz $\pm$ 10% for cap $\leq$ 1000 pF	
Q		<30 pF: Q $\geq$ 400+20 x Cap Value $\geq$ 30 pF: Q $\geq$ 1000	1.0 kHz $\pm$ 10% for cap > 1000 pF	
Insulation Resistance		10,000M Ω or 500M Ω - μ F, whichever is less	Voltage: 1.0Vrms $\pm$.2V	
Dielectric Strength		No breakdown or visual defects	Charge device with rated voltage for 60 $\pm$ 5 secs @ room temp/humidity	
Resistance to Flexure Stresses	Appearance	No defects	Deflection: 2mm Test Time: 30 seconds 1mm/sec 	
	Capacitance Variation	$\pm$ 5% or $\pm$.5 pF, whichever is greater		
	Q	Meets Initial Values (As Above)		
	Insulation Resistance	$\geq$ Initial Value x 0.3		
Solderability		$\geq$ 95% of each terminal should be covered with fresh solder	Dip device in eutectic solder at 230 $\pm$ 5°C for 5.0 $\pm$ 0.5 seconds	
Resistance to Solder Heat	Appearance	No defects, <25% leaching of either end terminal	Dip device in eutectic solder at 260°C for 60sec- onds. Store at room temperature for 24 $\pm$ 2 hours before measuring electrical properties.	
	Capacitance Variation	$\leq$ $\pm$ 2.5% or $\pm$.25 pF, whichever is greater		
	Q	Meets Initial Values (As Above)		
	Insulation Resistance	Meets Initial Values (As Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Thermal Shock	Appearance	No visual defects	Step 1: -55°C $\pm$ 2°	30 $\pm$ 3 minutes
	Capacitance Variation	$\leq$ $\pm$ 2.5% or $\pm$.25 pF, whichever is greater	Step 2: Room Temp	$\leq$ 3 minutes
	Q	Meets Initial Values (As Above)	Step 3: +125°C $\pm$ 2°	30 $\pm$ 3 minutes
	Insulation Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	$\leq$ 3 minutes
	Dielectric Strength	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 hours at room temperature	
Load Life	Appearance	No visual defects	Charge device with twice rated voltage in test chamber set at 125°C $\pm$ 2°C for 1000 hours (+48, -0). Remove from test chamber and stabilize at room temperature for 24 hours before measuring.	
	Capacitance Variation	$\leq$ $\pm$ 3.0% or $\pm$.3 pF, whichever is greater		
	Q (C=Nominal Cap)	$\geq$ 30 pF: Q $\geq$ 350 $\geq$ 10 pF, <30 pF: Q $\geq$ 275 +5C/2 <10 pF: Q $\geq$ 200 +10C		
	Insulation Resistance	$\geq$ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Load Humidity	Appearance	No visual defects	Store in a test chamber set at 85°C $\pm$ 2°C/ 85% $\pm$ 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied. Remove from chamber and stabilize at room temperature for 24 $\pm$ 2 hours before measuring.	
	Capacitance Variation	$\leq$ $\pm$ 5.0% or $\pm$.5 pF, whichever is greater		
	Q	$\geq$ 30 pF: Q $\geq$ 350 $\geq$ 10 pF, <30 pF: Q $\geq$ 275 +5C/2 <10 pF: Q $\geq$ 200 +10C		
	Insulation Resistance	$\geq$ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		

C0G (NP0) Dielectric

Capacitance Range

PREFERRED SIZES ARE SHADED

SIZE		0101*	0201		0402		0603					0805						1206							
Soldering		Reflow Only	Reflow Only		Reflow/Wave		Reflow/Wave					Reflow/Wave						Reflow/Wave							
Packaging		All Paper	All Paper		All Paper		All Paper					Paper/Embossed						Paper/Embossed							
(L) Length	mm (in.)	0.40 ± 0.02 (0.016 ± 0.0008)	0.60 ± 0.03 (0.024 ± 0.001)		1.00 ± 0.10 (0.040 ± 0.004)		1.60 ± 0.15 (0.063 ± 0.006)					2.01 ± 0.20 (0.079 ± 0.008)						3.20 ± 0.20 (0.126 ± 0.008)							
W) Width	mm (in.)	0.20 ± 0.02 (0.008 ± 0.0008)	0.30 ± 0.03 (0.011 ± 0.001)		0.50 ± 0.10 (0.020 ± 0.004)		0.81 ± 0.15 (0.032 ± 0.006)					1.25 ± 0.20 (0.049 ± 0.008)						1.60 ± 0.20 (0.063 ± 0.008)							
(t) Terminal	mm (in.)	0.10 ± 0.04 (0.004 ± 0.0016)	0.15 ± 0.05 (0.006 ± 0.002)		0.25 ± 0.15 (0.010 ± 0.006)		0.35 ± 0.15 (0.014 ± 0.006)					0.50 ± 0.25 (0.020 ± 0.010)						0.50 ± 0.25 (0.020 ± 0.010)							
	WVDC	16	25	50	16	25	50	16	25	50	100	200	16	25	50	100	200	250	16	25	50	100	200	250	500
Cap (pF)	0.5		A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J
	1.0	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J
	1.2	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J
	1.5	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J
1.8	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J	J
2.2	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J	J
2.7	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J	J
3.3	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J	J
3.9	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J	J
4.7	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J	J
5.6	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J	J
6.8	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J	J
8.2	B	A	A	C	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J	J
10	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
12	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
15	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
18	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
22	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
27	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
33	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
39	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
47	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
56	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
68	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
82	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
100	B	A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
120		A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
150		A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J
180		A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	N	N	J	J	J	J	J	J	J
220		A	A	C	C	C	C	G	G	G	G	G	J	J	J	J	N	N	J	J	J	J	J	J	J
270				C	C	C	C	G	G	G	G	G	J	J	J	J	N	N	J	J	J	J	J	J	J
330				C	C	C	C	G	G	G	G	G	J	J	J	J	N	N	J	J	J	J	J	J	J
390				C	C	C	C	G	G	G	G	G	J	J	J	J	N	N	J	J	J	J	J	J	J
470				C	C	C	C	G	G	G	G	G	J	J	J	J	N	N	J	J	J	J	J	J	J
560				C	C	C	C	G	G	G	G	G	J	J	J	J	N	N	J	J	J	J	J	J	J
680				C	C	C	C	G	G	G	G	G	J	J	J	J	N	N	J	J	J	J	J	J	J
750				C	C	C	C	G	G	G	G	G	J	J	J	J	N	N	J	J	J	J	J	J	J
820				C	C	C	C	G	G	G	G	G	J	J	J	J	N	N	J	J	J	J	J	J	J
1000				C	C	C	C	G	G	G	G	G	J	J	J	J	N	N	J	J	J	J	J	J	J
1200								G	G	G	G		J	J	J	J	P	P	J	J	J	J	J	J	J
1500								G	G	G	G		J	J	J	J	P	P	J	J	J	J	M	Q	P
1800								G	G	G	G		J	J	J	J	P	P	J	J	M	P	Q	P	P
2200								G	G	G	G		P	P	P	P	P	P	J	J	M	P	Q	P	P
2700								G	G	G	G		P	P	P	P	P	P	J	J	M	P	Q	P	P
3300								G	G	G	G		P	P	P	P	P	P	J	J	M	P	Q	X	P
3900								G	G	G	G		P	P	P	P	P	P	J	J	M	P	X	X	X
4700								G	G	G	G		P	P	P	P	P	P	J	J	M	P	X	X	X
5600													P	P	P	P			J	J	M	P	X	X	X
6800													P	P	P	P			M	M	M	P	X	X	X
8200													P	P	P	P			P	P	P	P	X	X	
Cap (uF)	0.010												P	P	P	P			P	P	P	P	X	X	
0.012													P	P	P	P			X	X	X	X	X	X	
0.015																			X	X	X	X	X	X	
0.018																			X	X	X	X	X	X	
0.022																			X	X	X	X	X	X	
0.027																			X	X	X	X	X	X	
0.033																			X	X	X	X	X	X	
0.039																			X	X	X	X	X	X	
0.047																			X	X	X	X	X	X	
0.068																			X	X	X	X	X	X	
0.082																			X	X	X	X	X	X	
0.1																			X	X	X	X	X	X	
WVDC		16	25	50	16	25	50	16	25	50	100	200	16	25	50	100	200	250	16	25	50	100	200	250	500
SIZE		0101*	0201		0402		0603					0805						1206							




Letter	A	B	C	E	G	J	K	M	N	P	Q	X	Y	Z
Max. Thickness	0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)
	PAPER						EMBOSSD							

C0G (NP0) Dielectric
Capacitance Range



PREFERRED SIZES ARE SHADED

SIZE		1210					1812					1825			2220			2225		
Soldering		Reflow Only					Reflow Only					Reflow Only			Reflow Only			Reflow Only		
Packaging		Paper/Embossed					All Embossed					All Embossed			All Embossed			All Embossed		
(L) Length	mm (in.)	3.20 ± 0.20 (0.126 ± 0.008)					4.50 ± 0.30 (0.177 ± 0.012)					4.50 ± 0.30 (0.177 ± 0.012)			5.70 ± 0.40 (0.225 ± 0.016)			5.72 ± 0.25 (0.225 ± 0.010)		
(W) Width	mm (in.)	2.50 ± 0.20 (0.098 ± 0.008)					3.20 ± 0.20 (0.126 ± 0.008)					6.40 ± 0.40 (0.252 ± 0.016)			5.00 ± 0.40 (0.197 ± 0.016)			6.35 ± 0.25 (0.250 ± 0.010)		
(t) Terminal	mm (in.)	0.50 ± 0.25 (0.020 ± 0.010)					0.61 ± 0.36 (0.024 ± 0.014)					0.61 ± 0.36 (0.024 ± 0.014)			0.64 ± 0.39 (0.025 ± 0.015)			0.64 ± 0.39 (0.025 ± 0.015)		
WVDC		25	50	100	200	500	25	50	100	200	500	50	100	200	50	100	200	50	100	200
Cap (pF)	3.9 4.7 5.6 6.8 8.2																			
	10 12 15	M	M	M	M	M	P	P	P	P	P									
	18 22 27	M	M	M	M	M	P	P	P	P	P									
	33 39 47	M	M	M	M	M	P	P	P	P	P									
	56 68 82	P	P	P	P	P	P	P	P	P	P									
	100 120 150	P	P	P	P	P	P	P	P	P	P									
	180 220 270	P	P	P	P	P	P	P	P	P	P									
	330 390 470	P	P	P	P	P	P	P	P	P	P									
	560 680 820	P	P	P	P	P	P	P	P	P	P									
	1000 1200 1500	P	P	P	P	P	P	P	P	P	P	M	M	M				M	M	P
	1800 2200 2700	P	P	P	P	P	P	P	P	P	P	M	M	M				M	M	P
	3300 3900 4700	P	P	P	P	P	P	P	P	P	P	Q	X	X	X		X	M	M	P
	5600 6800 8200	P	P	P	P	P	P	P	P	P	P	Y	X	X	X	X	X	M	M	P
Cap (µF)	0.010 0.012 0.015	P	P	X	X	X	P	P	Q	Q	Y	X	X	X	X	X	X	M	M	P
	0.018 0.022 0.027	X	X	Z	Z	Z	P	P	X	X	Y	X	X	X	X	X	X	M	M	Y
	0.033 0.039 0.047	X	Z	Z	Z	Z	Q	X	X	Z		X	X	Y	X	X		P	Y	Y
	0.068 0.082 0.1						Z	Z	Z	Z					Z			X	Z	
							Z	Z	Z	Z					Z			X	Z	
							Z	Z	Z	Z					Z			Z	Z	
WVDC		25	50	100	200	500	25	50	100	200	500	50	100	200	50	100	200	50	100	200
SIZE		1210					1812					1825			2220			2225		



Letter	A	B	C	E	G	J	K	M	N	P	Q	X	Y	Z
Max. Thickness	0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)
PAPER							EMBOSSD							

Looking for pricing, stock, or lifecycle information?

Click below to explore more details on WIN SOURCE:

⊖ [View 06035A471JAT2A](#) on WIN SOURCE

⊖ [AVX Corp/Kyocera Corp](#) Information

Optimize Your Supply Chain with WIN SOURCE Solutions

- ✓ Global Sourcing Solution
- ✓ Obsolete Management
- ✓ Cost Control Management
- ✓ Shortage Management
- ✓ Alternative Solution
- ✓ Excess Inventory Management